


**Amendments to Claims**

Claim 1 (currently amended): A polyacetal resin composition consisting essentially of (a) a polyacetal resin, and (b) one or more members of the group of odor-reducing additives consisting of

- (i) succinimide; and  
(ii) a low molecular weight primary or secondary amino compound of low volatility, containing at least one amino group and two or more carbon atoms, and having a pK<sub>b</sub> in the range of about 2 – 8, excepting and excluding those amino compounds described by the formula



wherein R<sup>4</sup>, R<sup>5</sup> and R<sup>6</sup> are selected from the class consisting of hydroxyalkyl groups having 1~4 carbon atoms and alkyl groups having 1~9 carbon atoms, and the R<sup>7</sup> and R<sup>8</sup> groups are selected from the class consisting of hydrogen and alkyl groups having 1~4 carbon atoms;

wherein the composition is characterized by a formaldehyde concentration at room temperature that is less than about 50% of the formaldehyde concentration of the polyacetal resin itself.

Claim 2 (original): A composition according to Claim 1 wherein the amino compound has a pK<sub>b</sub> in the range of about 4 – 8.

Claim 3 (original): A composition according to Claim 1 wherein the amino compound is characterized by T<sub>bp</sub> > T<sub>m</sub> – 60°C, where T<sub>bp</sub> is the boiling point of the amino compound and T<sub>m</sub> is the melting point of the polyacetal resin.

Claim 4 (currently amended): A composition according to Claim 1 wherein the amino compound is selected from the group consisting of ~~monoethanolamine~~, diethanolamine, ~~2-amino-2-ethyl-propanediol~~, ~~2-amino-2-~~


~~methyl propanol, tris(hydroxymethyl)aminomethane, ethyl *p*-aminobenzoate, methyl anthranilate, butyl *m*-aminobenzoate, and mixtures thereof.~~

Claim 5 (currently amended): A polyacetal resin composition consisting essentially of (a) a polyacetal according to Claim 1 resin, and (b) a low molecular weight primary amino compound of low volatility, containing at least one amino group and two or more carbon atoms, and having a pK<sub>b</sub> in the range of about 2-8; wherein the composition is characterized by a formaldehyde concentration at room temperature that is less than about 50% of the formaldehyde concentration of the polyacetal resin itself and wherein the amino compound is ~~selected from the group consisting of tris(hydroxymethyl)aminomethane, ethyl *p*-aminobenzoate, and mixtures thereof.~~

Claim 6. (original) A composition according to Claim 1 wherein the amino compound is present in the composition in an amount of about 0.01~10 parts by weight, per 100 parts by weight of the polyacetal resin.

Claim 7. (original) A composition according to Claim 1 wherein the polyacetal resin is an acetal copolymer.

Claim 8. (original) A composition according to Claim 1 further consisting essentially of an organic cyclic compound having an active imino group according to the formula



wherein R<sup>1</sup>, R<sup>2</sup> and R<sup>3</sup> are divalent organic radicals.

Claim 9. (original) A composition according to Claim 1 further consisting essentially of at least one additive selected from the group consisting of nucleating agents, mold release agents, surfactants, impact modifiers, reinforcing agents, anti-static agents, plasticizers, lubricants, fillers and colorants.

Claims 10-27 (canceled)

Claim 28. (original) A shaped article produced from a composition according to Claim 1.


Claims 29-31 (canceled)

Claim 32 (currently amended): A method for reducing the formaldehyde concentration of a part molded from a polyacetal resin, comprising

(a) forming a composition consisting essentially of (i) the polyacetal resin, and (ii) one or more members of the group of odor-reducing additives consisting of

(A)succinimide; and

(B)a low molecular weight primary or secondary amino compound of low volatility, containing at least one amino group and two or more carbon atoms, and having a pKb in the range of 2– 8; excepting and excluding those amino compounds described by the formula



wherein  $\text{R}^4$ ,  $\text{R}^5$  and  $\text{R}^6$  are selected from the class consisting of hydroxyalkyl groups having 1~4 carbon atoms and alkyl groups having 1~9 carbon atoms, and the  $\text{R}^7$  and  $\text{R}^8$  groups are selected from the class consisting of hydrogen and alkyl groups having 1~4 carbon atoms; wherein the amino compound of low volatility is characterized by  $T_{\text{bp}} > T_{\text{m}} - 60^\circ\text{C}$ , where  $T_{\text{bp}}$  is the boiling point of the amino compound and  $T_{\text{m}}$  is the melting point of the polyacetal resin; and

wherein the composition is characterized by a formaldehyde concentration at room temperature that is less than about 50% of the formaldehyde concentration of the polyacetal resin itself; and

(b) molding the part from the composition.

Claim 33 (currently amended): A method according to Claim 32 further comprising the step of selecting as the amino compound a member of the group consisting of ~~monoethanolamine~~, diethanolamine, ~~2-amino-2-ethyl-propanediol~~,

~~2-amino-2-methyl-propanol, tris(hydroxymethyl)aminomethane~~, ethyl *p*-aminobenzoate, methyl anthranilate, butyl *m*-aminobenzoate, and mixtures thereof.

Claims 34-38 (canceled)

Claim 39 (new): A method for reducing the formaldehyde concentration of a part molded from a polyacetal resin, comprising

- (a) forming a composition consisting essentially of (i) the polyacetal resin, and (ii) a low molecular weight primary amino compound of low volatility, containing at least one amino group and two or more carbon atoms, and having a pK<sub>b</sub> in the range of 2– 8; wherein the composition is characterized by a formaldehyde concentration at room temperature that is less than about 50% of the formaldehyde concentration of the polyacetal resin itself and wherein the amino compound is ethyl *p*-aminobenzoate; and
- (b) molding the part from the composition.